

# TIMBER SPECIES

## **African Mahogany – *Khaya ivorensis***

### Wood Appearance

**Colour** – Heartwood varies from light to deep reddish-brown

**Grain** – Straight grain to interlocked

### Wood Properties

**Density** – 540 kg/m<sup>3</sup>

**Durability** – Not Available

**Hardness** – Not Available

### Identification Features

**Sapwood** – Not distinguishable from the heartwood

**Heartwood** – Heartwood varies from light to deep reddish-brown

**Texture** – Moderately coarse texture to medium. Logs may have brittle heart or soft heart and cross fractures or heartbreaks.

### Wood Structure

**Growth Rings** – Not Available

**Vessels** – Not Available

**Parenchyma** – Not Available

**Rays** – Not Available

### Other Features

**Burning Splinter Test** – Not Available

**MASTER WOODTURNING**  
37 LANCASTER STREET  
INGLEBURN NSW 2565

**P: 02 9829 5000**  
**F: 02 9829 5100**  
E: [Sales@masterwoodturning.com.au](mailto:Sales@masterwoodturning.com.au)

*We do anything when it comes to wood*