

TIMBER SPECIES

Karri – *Eucalyptus diversicolor*

Wood Appearance

Colour – The heartwood varies from rich reddish browns through to pale pinks with the sapwood being a clearly distinguishable light yellow.

Grain – Considerable interlocked grain may be a feature

Wood Properties

Density – 900 kg/m³

Durability – Class 3 – Moderately resistant to decay when fully exposed to the weather, clear of the ground and well drained with free air circulation. Not recommended for in-ground use, or in external decking applications.

Hardness – Not Available

Identification Features

Sapwood – Clearly distinguishable light yellow

Heartwood – Varies from rich reddish browns through to pale pinks

Texture – Coarse

Wood Structure

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood