

River Red Gum – *Eucalyptus camaldulensis*

Wood Appearance

Colour – The heartwood is red to reddish brown in colour with the sapwood being distinctly paler.

Grain – Commonly interlocked with frequent gum veins

Wood Properties

Density – 900 kg/m³

Durability – Class 2 – highly resistant to decay when fully exposed to weather, clear of the ground and well drained with free air circulation. Moderately decay resistant in the ground.

Hardness – Not Available

Identification Features

Sapwood – Distinctly paler than the heartwood

Heartwood – Red to reddish brown

Texture – Moderately coarse and even

Wood Structure

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

Gum Veins - Frequent

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood