

# Myrtle – *Nothofagus cunninghamii*

## Wood Appearance

**Colour** – The heartwood is pale pink to deep red, occasionally with pale yellow-grey streaks. Sapwood is white to light pink.

**Grain** – Grain is mainly straight and occasionally wavy with clearly visible growth rings.

## Wood Properties

**Density** – 700 kg/m<sup>3</sup>

**Durability** – Class 4 – Suitable for use only in continuously dry situations under cover, well ventilated, clear of the ground and fully protected from the weather and dampness.

**Hardness** – Not Available

## Identification Features

**Sapwood** – Sapwood is white to light pink.

**Heartwood** – The heartwood is pale pink to deep red, occasionally with pale yellow-grey streaks.

**Texture** – Fine, uniform and smooth.

## Wood Structure

**Vessels** – Not Available

**Parenchyma** – Not Available

**Rays** – Not Available

## Other Features

**Burning Splinter Test** – Not Available

**MASTER WOODTURNING**  
37 LANCASTER STREET  
INGLEBURN NSW 2565

**P: 02 9829 5000**  
**F: 02 9829 5100**  
E: [Sales@masterwoodturning.com.au](mailto:Sales@masterwoodturning.com.au)

*We do anything when it comes to wood*