

Huon Pine

Lagarostrobos franklinii (formerly *Dacrydium franklinii*)

Wood Appearance

Colour – Light straw, ageing to dull yellow

Grain – Straight fine and even, sometimes with birds-eye figuring. Growth rings are conspicuous and usually wavy.

Wood Properties

Density – 550 kg/m³

Durability – Class 3 – Moderately resistant to decay when fully exposed to the weather, clear of the ground and well drained with free air circulation. Not recommended for in-ground use, or in external decking applications.

Hardness – Not Available

Identification Features

Sapwood – Not differentiated from the heartwood

Heartwood – Light straw, ageing to dull yellow

Texture – Close, uniform and smooth

Wood Structure

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood