

Silver Wattle – *Acacia dealbata*

Wood Appearance

Colour – Light brown to pink

Grain – Grain is usually straight. Growth rings are conspicuous

Wood Properties

Density – 650 kg/m³

Durability – Silver wattle is not included in AS 5604-2005 Timber - Natural durability ratings. It has good durability for decorative, architectural and structural applications internally but is not recommended for external use.

Hardness – Not Available

Identification Features

Sapwood – Not differentiated from the heartwood

Heartwood – Light brown to pink

Texture – Uniform and porous

Wood Structure

Vessels – Not Available

Parenchyma – Not Available

Rays – Not Available

Other Features

Burning Splinter Test – Not Available

MASTER WOODTURNING
37 LANCASTER STREET
INGLEBURN NSW 2565

P: 02 9829 5000
F: 02 9829 5100
E: Sales@masterwoodturning.com.au

We do anything when it comes to wood